

### Çelik İşlenebilirlik Oranları

AISI - SAE	EN	WNr.	TESLİM ŞEKLİ	İŞLENEBİLİRLİK ORANI %
12L14	11SMnPb30	1.0718	+C	170
1215	11SMn30	1.0715	+C	136
<b>1212</b>	<b>10S10</b>	<b>1.0711</b>	<b>+C</b>	<b>100</b>
1117	10S20	1.0721	+C	91
1137	36SMn14	1.0764	+C	72
1144	44SMn28	1.0762	+C+A	85
			+C	80
1008	DC01	1.033	+C	55
1010	C10E	1.1121	+C	55
1015	C15E	1.1141	+C	60
1016	C16E	1.1148	+C	70
1020	C22E	1.1151	+C	65
1025	C25E	1.1158	+C	65
1030	C30E	1.1178	+C	70
1035	C35E	1.1181	+C	65
1040	C40E	1.1186	+C	60
			+A+C	65
1045	C45E	1.1191	+C	55
			+C+A	72
			+A+C	55
1050	C50E	1.1206	+C	45
			+C+A	70
1055	C55E	1.1203	+A+C	55
1060	C60E	1.1221	+AC+C	60
4118	20MoCr4	1.7321	+C	60
4130	25CrMo4	1.7214	+A+C	70
4135	34CrMo4	1.722	+A+C	70
4140	42CrMo4	1.7225	+A+C	65
41L42	42CrMo4Pb		+A+C	77
4150	50CrMo4	1.7228	+A+C	55
4340	40NiCrMo7		+A+C	50
4615	17Cr3	1.7016	+C	65
4820	18CrNiMo7-6	1.6587	+A+C	50
5046	46Cr2	1.7006	+A+C	60
5115	16MnCr5	1.7131	+C	65
5120	20MnCr5	1.7147	+C	70
5132	34Cr4	1.7033	+A+C	70
5140	41Cr4	1.7035	+A+C	65
5150	46Cr2	1.7006	+A+C	60
52100	100Cr6	1.3505	+AC+C	40
6150	51CrV4	1.2241	+A+C	55
8620	20NiCrMo2-2	1.6523	+C	65
9254	54SiCr6	1.7102	+AC+C	45
9310	14NiCrMo13-4	1.6657	+A+C	50

